



A drainage figure of 6.80%/1.845 L/sec/m<sup>2</sup> has been calculated depending on the design of the sub- base and stone in the joints' We recommend 6mm of clean aggregate in the joints.

# MONAPAVE PERMEABLE 80 TECHNICAL SPECIFICATION

<b>Size and Form</b>	200 x 100 x 80mm
<b>Product Code</b>	PV042
<b>Unit Dry Weight</b>	3.20 kg
<b>Density</b>	2200 kg m <sup>3</sup>
<b>Standard Compressive Strength</b>	37.0 N/mm
<b>Abrasion Resistance</b>	20 Class 4
<b>Unpolished Slip Resistance</b>	78 (USRV)
<b>Available Colours</b>	Brindle, Terracotta, Buff, Charcoal, Natural
<b>Units Per M2</b>	50 No
<b>Pack Quantity Pack Coverage</b>	360 No 7.2m <sup>2</sup>
<b>Manufacturing Category</b>	BS EN 771-3:2003 Cat. D1
<b>FPC Quality Standard Environmental Standard</b>	BS EN ISO 9001:2015 BS EN ISO 14001:2015



**MONA  
PRECAST LTD**  
Anglesey, Gaerwen  
Industrial Estate  
LL60 6HR

[www.monaprecast.com](http://www.monaprecast.com)

[info@monaprecast.com](mailto:info@monaprecast.com)