



# MONAGREEN BLOCK

## TECHNICAL SPECIFICATION

<b>Size and Form</b> <i>Blocks must be laid voids down onto a full bed of mortar</i>	440 x 215 x 100mm Cellular
<b>Product Code</b>	MG001
<b>Dry Density</b>	1800 kg/ m <sup>3</sup>
<b>Thermal Conductivity (Protected)</b>	0.59 W/mk
<b>Thermal Resistance (Protected)</b>	0.165 m <sup>2</sup> k/w
<b>Mean Dry Weight</b>	14.0 kg
<b>Available Compressive Strength</b> <i>Measured over full bed area &amp; voids</i>	3.6 / 7.3 N/ mm <sup>2</sup>
<b>Moisture Movement</b>	0.03%
<b>Sound Reduction (lwt plaster)</b>	47 Rw (C;Ctr) dB
<b>Notional Fire Resistance</b>	2 Hours
<b>Recycled Aggregate Content</b>	≥ 80%
<b>Manufacturing Category</b>	BS EN 771-3:2003 Cat. D1
<b>FPC Quality Standard</b> <b>Environmental Standard</b>	BS EN ISO 9001:2015 BS EN ISO 14001:2015

**MONA  
PRECAST LTD**  
Anglesey, Gaerwen  
Industrial Estate  
LL60 6HR

[www.monaprecast.com](http://www.monaprecast.com)

[sales@monaprecast.com](mailto:sales@monaprecast.com)